

## Technical Data Sheet

### Capatue™ SCA-E87M

#### Abstract

SCA-E87M is an epoxy functional silane suitable for use as adhesion promoters in polysulfide, urethane, epoxy and acrylic caulks sealants and adhesives.

#### Chemical Name

3-Glycidoxypropyltrimethoxysilane

#### Synonyms

[3-(2,3-Epoxypropoxy)propyl]trimethoxysilane;  
 Glycidyl 3-(trimethoxysilyl)propyl ether

#### CAS Registry Number

2530-83-8


#### EINECS

219-784-2

#### Molecular Formula

$C_9H_{20}O_5Si$

#### Molecular Structure



#### Molecular Weight

236.34

#### Equivalents

Product	Supplier
Silquest® A-187	Momentive (formerly OSi Specialties)
Z-6040	Dow Corning
Dynasylan® GLYMO	Evonik (formerly Degussa)
GENIOSIL® GF 80	Wacker
KBM-403	Shin-Etsu

[Http://www.capatue.com](http://www.capatue.com) E-mail: [info@capatue.com](mailto:info@capatue.com)

Tel: +86-25-8637 1192, 8637 1193 Fax: +86-25-8637 1191 ext. 0

Add: Block E4, Zidong Industry Park, 2 Zidong Road, Maqun Town, Qixia Dist., Nanjing, Jiangsu, China, 210023



Sila-Ace <sup>®</sup> S510	Chisso
E6720	UCT (United Chemical Technologies, Inc)

**Typical Properties**

Index	Value
Appearance	Colorless, transparent liquid
GC Purity, %	≥ 99
Color, Pt-Co	≤ 30
Specific Gravity (ρ <sub>20</sub> ), g/cm <sup>3</sup>	1.060
Boiling Point (760mmHg), °C	290
Refractive Index (n <sub>D</sub> <sup>25</sup> )	1.427
Flash Point, °C	110
Free Chlorine, ppm	≤ 50
Solubility	Soluble in water after hydrolysis, alcohol, acetone, and most aliphatic esters at normal application levels fewer than 5%. Hydrolysis releases methanol.

**Applications and Performance**

1. Enhances electrical properties of epoxy electronic encapsulant and packaging materials, resulting from improved bonding between resin and substrate filler.
2. Stable in waterborne applications such as acrylic and vinyl acrylic caulks and emulsion adhesive and coating.
3. Improved adhesion to glass, concrete and metal substrate can be obtained in epoxy, polysulfide, urethane and acrylic bases adhesive, sealants and caulks.
4. Improves mechanic strength of glass fiber reinforcement or minerals filled engineering plastic especially PA.

### Packing

The regular packing of this product is 25kg plastic pail, 200L steel drums and 1000L immediate bulk container.

### Storage and Shelf Life

Should be stored in dry, cool, ventilated room; keep away from water, moisture, high temperature and fire. This product has a shelf life of at least 12 months if stored in tightly closed original container at room temperature.

If this product is kept beyond the shelf life recommend on the product label, it is not necessarily unusable, but a quality control should be performed on the properties relevant to the application.

### Product Safety and Handling

When considering the use of any Capatue products in a particular application, you should read our latest Material Safety Data Sheets (MSDS) thoroughly for handling instructions, personal protective equipment if necessary, other safety issue and toxicological data as well as for information on proper transportation, storage and use to ensure that the use you intend can be accomplished safely. Our latest Material Safety Data Sheets (MSDS) and other product safety information are available at [www.capatue.com](http://www.capatue.com) or upon request, from our customer service department.

Use of other material in conjunction with Capatue products may require addition precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

**This product is for industry use only; it is neither tested nor represented as suitable for food, medical or pharmaceutical uses.**

### Limited Warranty Information

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that Capatue's products are safe, effective, and fully satisfactory for the intended end use.

Suggestions of use shall not be taken as inducements to infringe any patent.

**Capatue's sole warranty is that the product will meet the Capatue sales specifications in effect at the time of shipment.**

**Your exclusive remedy for breach of such warranty is limited to refund of**

[Http://www.capatue.com](http://www.capatue.com) E-mail: [info@capatue.com](mailto:info@capatue.com)

Tel: +86-25-8637 1192, 8637 1193 Fax: +86-25-8637 1191 ext. 0

Add: Block E4, Zidong Industry Park, 2 Zidong Road, Maqun Town, Qixia Dist., Nanjing, Jiangsu, China, 210023

purchase price or replacement of any product shown to be other than as warranted.

Capatue specifically disclaims any other express or implied warranty of fitness for a particular purpose or merchantability.

Capatue disclaims liability for any incidental or consequential damages.

Customer must do enough tests before their regular production to ensure that our product is suitable for their specific application.